

Sutherland Welles Ltd.®

Sustainable, natural & earth-friendly Polymerized Tung Oil wood finishes.



Murdoch's Floor Instructions

Applicator Options

Rag: Scott® blue paper shop towels

Brush: Natural white china bristle brush (thin coats only)

3M™ Synthetic Maroon BCP

Short Napped Synthetic Applicator

Cure Test

Lightly sand several inconspicuous areas. A fine, white powder indicates that you can safely apply another coat.

Murdoch's Uralkyd 500 Floor Finish

Murdoch's Hard Sealer applied as the initial coats enhance the grain definition that is often characteristic of the wood species chosen for drums. The final appearance is produced by the choice of topcoat. Murdoch's Uralkyd 500 Matte, Satin or Gloss provide maximum protection. We recommend this for high moisture areas such as kitchens and bathrooms.

Uralkyd Floor Instructions

step 1:

- Apply Murdoch's Hard Sealer
- Don't wipe
- Let cure 2-3 hours

step 2:

- Sand 400 grit or **new** screen 120/150 grit or **new** synthetic 3M™ maroon BCP (Between Coat Pad)
- Vacuum & tack surface
(use Mineral Sprits on a rag to clean surface)

step 3:

- Apply Murdoch's Hard Sealer
- Don't wipe
- Let cure 4-6 hours

step 4:

- Sand 400 grit or **used** screen 120/150 grit or **used** synthetic 3M™ maroon BCP (Between Coat Pad)
- Vacuum & tack surface

step 5:

- Apply Murdoch's Uralkyd Matte, Satin or Gloss
- Let cure 24 hours

step 6:

- Sand 600 grit or **used** screen 120/150 grit or **used** synthetic 3M™ maroon BCP (Between Coat Pad)
- Vacuum & tack surface

step 7:

- Apply Murdoch's Uralkyd Matte, Satin or Gloss
- Let cure 24 hours

Helpful Hint!

Tips During Finishing

- Do not roll the topcoat.
- Minimize loading the brush/applicator. You want to flow on a thin even coat.
- Avoid rigorous brushing. The finish will level on its own.
- If you have bubbles in coat work them to other areas as they won't go away. They will burst and create marks in the cured surface.
- If using Satin or Matte, make sure to stir the product periodically while coating to distribute the flattening agent evenly.

Tips Post Finishing

- Allow the floor to remain unused for 72 hours for the surface to become harder and more resistant to damage.
- If this isn't practical covering the floor with contractors paper is the next best option if other trades people need to access the area.
- Allow at least 48 hours after last application prior to covering.
- Do not tape any covering directly to the finish.
- No rugs should be laid for 2 weeks to allow thorough curing of the finish.